

PS20 - Repolish Stone - Small Areas

Repolish Small Areas (Single Tiles, Table Tops, Bar Tops, Tables etc) of Lightly Etched or Scratched Calcium Based Stone - Marble, Limestone, Travertine etc

PRODUCT: ReShine™

EQUIPMENT: Pure soft cotton or terry towel cloth, spray bottle with clean water, absorbent paper or towels;
NOTE: Variable speed hand held buffer & a soft bonnet for larger areas or quicker results



PRECAUTIONS:

1. Read entire label, SDS & technical bulletin before using;
2. Wear appropriate gloves, skin & eye protection;
3. Use when surface temperature is between 4°C & 32°C;
4. Do **NOT** allow product to come in contact with any non-recommended surfaces;
5. Surface must be clean, dry and free from any existing coating sealers or other coatings;

PROCEDURE:

1. **SHAKE WELL BEFORE USING;**
2. Apply a small amount of Re-Shine™ (1-2 tablespoons) directly to etched or scratched area;
3. Mist a small amount of water onto Re-Shine™
4. Buff with soft cotton or terry towel until cream becomes clear and nearly dries;
5. **DO NOT ALLOW TO DRY ON SURFACE**
6. Re-wet surface with plenty of water to flush;
7. Polish completely dry with clean towels;
8. Repeat the process as necessary;
9. For larger areas or quicker results, you may use a variable speed hand held buffer with a soft bonnet or a white polishing pad.

NOTE: Surface should then be sealed with an appropriate Aqua-Seal STS™ sealer to provide stain resistance and ease ongoing maintenance - refer to our website www.aqua-seal.com.au;

SAFETY DIRECTIONS: **CORROSIVE - CONTAINS POTASSIUM OXALATE**

1. Wear protective gloves, eye & skin protection when using.

Note A: Severely scratched, damaged or worn polished stone may require professional restoration by diamond grinding.

Note B: Not suitable for some green and black marbles, granite, ceramic or porcelain tile;;

Note C: For repolishing larger floor areas, use Aqua Seal Polish Pro™ or Aqua Seal 5X Pro™. See Aqua Seal Problem Solver #21.

Note D: Use Aqua-Seal AquaGuard™ on tabletops, benchtops and other non-traffic areas to enhance the lustre of the polished finish.

This recommendation is intended as a general guideline. The actual procedure requirements, dilution ratios, dwell time etc may vary depending on type of surface, method of application and severity of the problem.

READ PRODUCT LABEL INSTRUCTIONS, TECHNICAL BULLETIN & SDS THOROUGHLY BEFORE USING. ALWAYS TEST FIRST.

KEEP SURFACE CLEAN AND DRY TO REDUCE THE POSSIBILITY OF SLIP & FALL ACCIDENTS AND INJURIES