

PS02 - Remove Grout Haze - Heavy

Remove Heavy Grout Haze from Porcelain or Ceramic Tiles

PRODUCT: OXITREAT HD™

EQUIPMENT: AquaBug Cleaning Kit, Scrub pad or brush, broom, bucket, clean water and cotton towels. Optional: Scrub machine, wet-dry vac.



PRECAUTIONS:

1. Read entire label, SDS & technical bulletin before using;
2. Wear appropriate skin & eye protection;
3. Use when surface temperature is between 4°C & 32°C;
4. Do not allow product to contact any non-recommended surfaces;
5. Take care when using on dark coloured grout or stone;

PROCEDURE:

1. Sweep, vacuum, or wipe surface;
2. Slightly pre-wet surface with clean water;
3. Dilute [OxiTreat HD™](#) depending on the severity of the problem:
 - a) **LIGHT:** Dilute 1 part [OxiTreat HD™](#) to 15 parts clean water.
 - b) **MODERATE:** Dilute 1 part [OxiTreat HD™](#) to 10 parts clean water.
 - c) **HEAVY:** Dilute 1 part [OxiTreat HD™](#) to 5 parts clean water
 - d) **EXTREME:** Dilute 1 part [OxiTreat HD™](#) to 3 parts clean water.
4. Carefully apply the solution to surface with a sponge or a mop;
5. Allow minimum dwell time of 10 minutes. Longer dwell time may be required.
6. **DO NOT ALLOW THE PRODUCT TO DRY ON THE SURFACE;**
7. Scrub with a white nylon pad or scrub machine;
8. Remove the dirty solution with a wet vac or mop;
9. Rinse thoroughly with clean water;
10. Repeat the process as necessary.

Note 1: Heavily soiled areas may require longer dwell time and/or stronger solution.

Note 2: Add [MicroScrub™](#) to standing solution just prior to scrubbing to boost performance where required

Note A: Do not use [OxiTreat HD™](#) on marble, limestone, travertine or on other acid-sensitive tile or stone.

Note B: Use [MicroScrub™](#) to remove grout haze from polished natural stone & acid sensitive surfaces - see [Problem Solver #3](#).

Note C: For high solids latex modified grouts mixing a dilution of [OxiTreat HD™](#) and [Strip-It™](#) may be required. See [Problem Solver #4](#)

This recommendation is intended as a general guideline. The actual procedure requirements, dilution ratios, dwell time etc may vary depending on type of surface, method of application and severity of the problem.

READ PRODUCT LABEL INSTRUCTIONS, TECHNICAL BULLETIN & SDS THOROUGHLY BEFORE USING. ALWAYS TEST FIRST.

KEEP SURFACE CLEAN AND DRY TO REDUCE THE POSSIBILITY OF SLIP & FALL ACCIDENTS AND INJURIES

