

# PS17 - Remove Enhance'N'Seal Residue

Remove Partial Cured Enhance'N'Seal Residue or After 48 hours of Application

**PRODUCT:** **STRIP-IT™**



- EQUIPMENT:**
- AquaBug Cleaning Kit;
  - Stripping pad or brush;
  - Broom
  - Bucket
  - Clean water;
  - Cotton towels.
  - Wet vac;
  - Optional: Scrub machine

- PRECAUTIONS:**
1. Read entire label, SDS & technical bulletin before using;
  2. Wear appropriate gloves, skin & eye protection and use in a well ventilated area or use an appropriate mask;
  3. Use when surface temperature is between 4°C and 32°C.
  4. Do not mix with other chemicals or allow product to come in contact with any non-recommended surfaces;
  5. Floor will get slippery during process. Take appropriate precautions to prevent slips or falls;
  6. Will affect sealers, coatings, floor finishes and painted surfaces.

- PROCEDURE:**
1. Sweep, vacuum, or wipe surface;
  2. Carefully apply a liberal amount of Strip-It™ to a small manageable area of up to 4m<sup>2</sup>. Use neat. Do NOT dilute;
  3. Spread with a roller, mop, sponge or brush;
  4. Allow product to dwell minimum 1 hour without drying or until coating or residue softens.
  5. DO NOT ALLOW PRODUCT TO DRY ON THE SURFACE - ADD MORE PRODUCT AS REQUIRED;
  6. Agitate with solvent resistant scrub pads, scrub brush or scrub machine;
  7. Remove the residue with a wet vac. If residue is thick, remove with clean, absorbent white cotton towels, a scoop or shovel;
  8. Rinse thoroughly with clean water; (See \* Important Note)
  9. Repeat the process as necessary;

- NOTE:**
1. To help with residue removal, apply XtremeClean™ diluted 1 part with 5 parts water to the surface after Step 8. Allow dwell time of 5-10 minutes then scrub or agitate. Remove with wet vac then rinse thoroughly. Allow to fully dry.
  2. Allow at least a 48 hour drying time before applying any sealers, coatings or floor finishes. Always do a test area first before applying to whole area.

**LIMITATIONS:** Removal of thick coatings may require multiple applications.

**Note A:** You must then re-apply Enhance'N'Seal as per label instructions. Patchiness can occur.

**Note B:** For Enhance'N'Seal residue that has cured, contact Aqua-Seal STS Technical Services.

This recommendation is intended as a general guideline. The actual procedure requirements, dilution ratios, dwell time etc may vary depending on type of surface, method of application and severity of the problem.

READ PRODUCT LABEL INSTRUCTIONS, TECHNICAL BULLETIN & SDS THOROUGHLY BEFORE USING. ALWAYS TEST FIRST. KEEP SURFACE CLEAN AND DRY TO REDUCE THE POSSIBILITY OF SLIP & FALL ACCIDENTS AND INJURIES